



ATMY ANALYTICAL LABS PVT.LTD.

I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com, www.atmylabs.com

- Testing
- Research
- Innovation

TEST REPORT

Report No.: 2107100075

Page 1 of 10
Date: 05-08-2021


Issued To:

M/s GEALAN PVT. LTD.

1ST FLOOR, DOOR NO. - 1-18/HIE/NE-2, HOLIDAY INN EXPRESS
SUITS, NANAKRAMGUDA, GACHIBOWLI, RANGA REDDY
TELANGANA - 50032

Sample Description : SLIDING FRAME 2 TRACK 60 MM SERIES
Sample Received Date : 10-07-2021
Sample Drawn By : Client
Specification : **BS 476: Part-7:1997 & BS 476: Part 5:1979**
Test Requested : Fire Resistance & Ignitability Test
Test Method : BS 476-Part-7:1997 & BS 476-Part-5:1979.
Test Result : Refer to Attached Pages.

SAMPLE PICTURE



Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Govt. Approved Laboratory
ISO 9001 : 2015, ISO 14001:2015 & OHAS 1800:2007 Certified Laboratory

Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01





ATMY ANALYTICAL LABS PVT.LTD.

I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com, www.atmylabs.com

- Testing
- Research
- Innovation

TEST REPORT

Report No.: 2107100075

Page 2 of 10
Date: 05-08-2021

I. FIRE TEST (as per Std. BS 476-part-7:1997)

Fire Resistance

Test Performed on : 12-07-2021 to 15-07-2021

Sample Description:

Product: uPVC Profile (Sliding Frame 2 Track 60mm Series)
Specification: - -
Sample Quantity: 02
Sample ID: 2107100075
Date of sample received: 10.07.2021
Date of Test Performed: 12.07.2021



"This test report is for the exclusive use of Atmy clients and is provided pursuant to the agreement between Atmy and its client. The laboratory will not be liable to any party, other than to the clients with the agreement, for any loss, expense or damage occasioned by the use of this report. Total liability of laboratory is limited to the invoiced amount only. This report cannot be used as evidence in a court of law without the written approval of Atmy".

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.

Govt. Approved Laboratory

ISO 9001 : 2015, ISO 14001:2015 & OHAS 1800:2007 Certified Laboratory

Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01





ATMY ANALYTICAL LABS PVT.LTD.

I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com, www.atmylabs.com

- Testing
- Research
- Innovation

TEST REPORT

Report No.: 2107100075

Page 3 of 10
Date: 05-08-2021

CONTENTS

PAGE NO.

SUMMARY

04

TEST DETAILS

05

TEST RESULTS

06

CLASSIFICATION CRITERIA

07

CONCLUSION

07

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Govt. Approved Laboratory
ISO 9001 : 2015, ISO 14001:2015 & OHAS 1800:2007 Certified Laboratory

Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01





ATMY ANALYTICAL LABS PVT.LTD.

I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com, www.atmylabs.com

- Testing
- Research
- Innovation

TEST REPORT

Report No.: 2107100075

Page 4 of 10
Date: 05-08-2021

1.0 SUMMARY

The objective of test was to determine of surface spread flame classification of the product "uPVC profile" in accordance with BS 476 Part – 7:1997. The test was performed in accordance with the procedures specified in the standard (BS 476 Part-7:1997) and the specimens were tested in the form of a composite. Test result of the product depicted that the sample tested has "Class -1" surface spread of flame in accordance with the class specified in the standard. The detailed results are summarized in the table-1.

Remarks:

The test results relate only to the behavior of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire Hazard of the product in use.

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Govt. Approved Laboratory

ISO 9001 : 2015, ISO 14001:2015 & OHAS 1800:2007 Certified Laboratory

Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01





TEST REPORT

Report No.: 2107100075

Page 5 of 10
Date: 05-08-2021

2.0 TEST DETAILS

2.1 Conditioning of Specimen:

Prior to the test, the specimens were prepared and conditioned in accordance with standard at a temperature $23 \pm 2^{\circ}\text{C}$ and relative humidity of $50 \pm 5\%$.

2.2 Form in which the specimens were tested:

Composite

2.3 Exposed faces:

The one face of the specimens was exposed to the heating conditions of the test.

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.





ATMY ANALYTICAL LABS PVT.LTD.

I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com, www.atmylabs.com

• Testing
• Research
• Innovation

TEST REPORT

Report No.: 2107100075

Page 6 of 10
Date: 05-08-2021

3.0 TEST RESULTS

3.1 The test results for individual samples are given in Table-1 below:

Table -1

Specimen No.	1	2	3	4	5	6
Spread of flame at first 1.5 minutes (mm)	55	58	55	57	54	57
Distance (mm)	Time of spread of flame to indicated distance (minutes : seconds)					
75 165 190 215 240 265 290 375 455 500 525 600 675 710 750 785 825						
Time of maximum spread of flame (minutes, seconds)	01:02	01:02	01:03	01:03	01:02	01:02
Distance of maximum spread of flame (mm)	69	69	70	70	70	69
Comments	None					

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Govt. Approved Laboratory

ISO 9001 : 2015, ISO 14001:2015 & OHAS 1800:2007 Certified Laboratory

Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01





TEST REPORT

Report No.: 2107100075

Page 7 of 10
Date: 05-08-2021

4.0 CLASSIFICATION CRITERIA

4.1 Classification of Surface spread of flame

Classification	Spread of flame at 1.5 min.		Final spread of flame	
	Limit (mm)	Limit for one specimen in sample (mm)	Limit (mm)	Limit for one specimen in sample (mm)
Class 1	165	165 + 25	165	165 + 25
Class 2	215	215 + 25	455	455 + 45
Class 3	265	265 + 25	710	710 + 75
Class 4	Exceeding the limits for class 3			

5.0 CONCLUSION:

In accordance with the class definitions specified in the standard, the test results shows that the sample tested has **"Class -1"** surface spread of flame.

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.





ATMY ANALYTICAL LABS PVT.LTD.

I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com, www.atmylabs.com

- Testing
- Research
- Innovation

TEST REPORT

Report No.: 2107100075

Page 8 of 10
Date: 05-08-2021

II. IGNITABILITY TEST (as per Std. BS 476:part 5:1979)

Ignitability Test

Test Performed on : 02-08-2021 to 05-08-2021

SAMPLE DESCRIPTION:

Product: uPVC Profile (Sliding Frame 2 Track 60mm Series)
Specification: - -
Sample Quantity: 02
Sample ID: 2107100075
Date of sample received: 10.07.2021
Date of Test Performed: 05.08.2021



Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.

Govt. Approved Laboratory

ISO 9001 : 2015, ISO 14001:2015 & OHAS 1800:2007 Certified Laboratory

Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01





ATMY ANALYTICAL LABS PVT.LTD.

I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com, www.atmylabs.com

- Testing
- Research
- Innovation

TEST REPORT

Report No.: 2107100075

Page 9 of 10
Date: 05-08-2021

TEST PURPOSE:

To determine the ignitability characteristics of the exposed surface of essentially flat, rigid or semi-rigid building materials, UPVC profile or composites, when tested in the vertical position to the specified in British Standard 476: Part 5:1979 "Method of test for ignitability".

TEST CONDITIONING:

Three specimens were conditioned for 48 hours at temp. $23 \pm 2^\circ\text{C}$ and relative humidity $50 \pm 5\%$.

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Govt. Approved Laboratory
ISO 9001 : 2015, ISO 14001:2015 & OHAS 1800:2007 Certified Laboratory

Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01





ATMY ANALYTICAL LABS PVT.LTD.

I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com, www.atmylabs.com

- Testing
- Research
- Innovation

TEST REPORT

Report No.: 2107100075

Page 10 of 10
Date: 05-08-2021

OBSERVATION:

Description	Specimens			Requirement	Conformity
	1	2	3		
1. Time of flaming removal of test flame	0	0	0	Not more than 10 sec.	Yes
2. Burning of the test specimen extending to the edges	No	No	No	Do not extent to any edge during flame application or within 10 sec period after removal of the test flame.	Yes

REMARKS: The above sample conforms to as per BS 476: Part 5: 1979 with respect to above test.

-----End of Report-----



D. Kumar
QUALITY MANAGER
Authorised Signatory

Authentication: To Check authenticity of Test report (s), Scan QR code to get original data.



Govt. Approved Laboratory

ISO 9001 : 2015, ISO 14001:2015 & OHAS 1800:2007 Certified Laboratory

Terms & Conditions:-

1. Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed. 2. Sample analysis conducted on as received basis and followed by customer description unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 5. The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 6. Total liability of our laboratory is limited to the invoiced amount only. 7. This report cannot be used as an evidence in a court of law without the written approval of the laboratory.

MSF 5.10.01

